

# Large Format Media Product Information Document

you can  
**Canon**

## Glossy Photo Paper – 170 g/m<sup>2</sup> - 6058B

Product Name	Grammage / (g/m <sup>2</sup> )	Thickness (µ)	Width / mm	Length / m	Mercury Code (EAN128)	Article number	Canon iPF5100	Canon iPF6100	Canon iPF6200	Canon iPF6300	Canon iPF6350	Canon iPF6000S	Canon iPF6300S	Canon iPF8100	Canon iPF8300	Canon iPF8000S	Canon iPF8300S	Canon iPF9100	Canon iPF9000S	Canon iPF510	Canon iPF610	Canon iPF605	Canon iPF650	Canon iPF655	Canon iPF710	Canon iPF720	Canon iPF750	Canon iPF755	Canon iPF810	Canon iPF815	Canon iPF820	Canon iPF825	Canon LP17	Canon LP24		
Glossy Photo Paper	170	172	610	30	6058B002AA	97003327	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V	V
	170	172	914	30	6058B003AA	97003328								V	V	V	V	V	V						V	V	V	V	V	V	V	V	V	V		
	170	172	1067	30	6058B004AA	97003329								V	V	V	V	V	V											V	V	V	V	V		



**Description:** This top quality photo inkjet paper has a quality photo coating for high grade natural colour prints of graphic pictures, presentations and photos. The paper is instant dry, is smudge resistant and provides good colour density and excellent image sharpness. This paper is compatible with a large range of dye and pigment digital printing systems, and is the most ideal product for users who need top quality photographic re-productions.

**Features:** Extremely quick drying, dye and pigment ink compatible, good colour density, excellent image sharpness, smudge resistant, lamination not necessary, easy handling.

**Applications:** Photography, portraits, posters, graphic art reproductions, exhibition graphics, indoor and outdoor signage.

### Physical Properties:

Weight	170 g/m <sup>2</sup>	±7
Caliper	172 µm	±5
Curl at 23 °C, 50% RH	0 mm	±8
Gloss (Tappi) 75°	70	±5
Opacity	91,0%	
Colour (CIE Lab) D50 /2°	L* 95.02	±0.5
	a* 1.05	±0.5
	b* -8.24	±0.8

**Printing :** For optimum results select the best possible print settings.  
Advised Driver / panel settings: Glossy Photo Paper 170gsm / GlossyPhoto 170g

**Finishing:** To add surface protection from dirt, abrasion and gas-fading, lamination is recommended. Although ink drying is virtually immediate, it is still recommended to allow a waiting time of approximately 3 hours before lamination. In order to prevent moisture ingress and paper splitting, lamination with a 5-6 mm encapsulated edge is also recommended. Laminate must be evenly applied to the print in order to avoid curling. Both hot and cold lamination is possible.

### Ideal Storage Conditions:

Store paper only in original boxes, out of direct sunlight and under normal climatic conditions ( 23 °C, 50% RH ) until ready to use. Allow material to adapt to room conditions before use. Papers can absorb moisture in humid conditions or lose moisture in low humidity conditions. Highly humid conditions make the ink drying time longer and this could interfere with proper laminate adhesion.

### Shelf Life:

2 years from shipping date when stored under ideal conditions (see above )

'A Whole Wide World of Media Excellence'