

Photo Papers

Toner
Water
(eco) Solvent
UV Curable
Latex

IJM263 Instant Dry Photo Paper, Satin 260 g/m²

Product Description Instant-dry, satin, bright white photo paper with a microporous coating, on a high-opacity heavy PE-coated base.

Physical Properties

Thickness (µm)	245 ± 20	ISO 534	Brightness (%)	92.7	ISO 2471-1
Weight (g/m ²)	255 ± 7	ISO 536	L*, a*, b*	93.3; 1.8; -8.9	DIN 13655
Opacity (%)	98.8	ISO 2471			

Applications/features

- High-quality photos
- Indoor signage (posters, point of purchase)
- Exhibition graphics
- Short-term outdoor signage (when laminated)
- Instant dry
- Excellent colour reproduction
- Bright white appearance
- High colour density and image sharpness
- Good lamination properties

Available Widths (mm)

3"core + 2"adapter	610	914	1067	1270	1524					
--------------------	-----	-----	------	------	------	--	--	--	--	--

Refer for our current offering to mediaguide.oce.com

Storage Conditions

Shelf life: 2 years, Temperature 15-25°C, Relative Humidity 30-70%.
 Repack opened rolls when not in use.

Print Conditions

Best results are obtained at 23°C and 50% RH.
 Higher humidity will increase drying time, low humidity may cause curling.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste is not suitable for recycling.

Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
yes	yes	no	

Outdoor Use

This photo paper is not suitable for outdoor use. Short time outdoor use possible only when laminated.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
 Check availability of profiles for your printer on mediaguide.oce.com



**Processing
Guidelines**

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.
Keep out of direct sunlight.
Side to be printed is the outer side of the roll.
Use of gloves is recommended.
Dye inks on microporous coated products can exhibit some fading (apart from UV) due to its open structure. Gases like Ozone cause this phenomenon. Lamination will solve this issue.

Lamination guidelines

Immediate lamination possible.
One-sided lamination may cause curling.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.