

Uncoated Papers

Toner

CrystalPoint

(eco) Solvent

UV Curable

Latex

LFM116 Top Label Paper - FSC® 75 g/m²

Product Description

A high white, smooth, FSC-certified, uncoated paper for high quality drawings and posters.

Physical Properties

| | | | | | |
|----------------------------|------|----------|--------------------|-----|------------|
| Weight (g/m ²) | 75 | | Brightness (%) | 113 | D65/10° |
| Opacity (%) | 93 | ISO 2471 | Whiteness (%) | 168 | CIE D65/10 |
| Bulk (cm ³ /g) | 1.39 | ISO 534 | Roughness (ml/min) | 200 | Bendtsen |

Applications/features

High quality CAD drawings and Posters
FSC certified
EU Ecolabel
ISO 9706 standard for permanence
EMAS and ISO 14001 certified

Available Widths (mm)

| | | | | | | | | | | |
|--------|-----|-----|-----|-----|-----|-----|--|--|--|--|
| 3"core | 297 | 420 | 594 | 620 | 841 | 914 | | | | |
|--------|-----|-----|-----|-----|-----|-----|--|--|--|--|

Refer for our current offering to mediaguide.oca.com

Storage Conditions

Shelf life: 2 years, Temperature 21°C, Relative Humidity 50%
Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

Print Conditions

Best results are obtained between 20-27°C and 30-60% RH.
Refer also to printer specifications.

Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste suitable for recycling.

Lamination Compatibility

| | | | |
|------|------|-----|-----------------------------------|
| Cold | Warm | Hot | Cold: pressure sensitive |
| yes | No | no | Warm: heat activated: 85°C - 95°C |
| | | | Hot: heat activated: 105°C -130°C |


Outdoor Use

This uncoated paper is developed for indoor use.

Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.
Check availability of profiles for your printer on mediaguide.oca.com

Environmental Certification



Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing.
It is recommended to handle the media with cotton gloves. Make sure that the media does not come into contact with grease, oil, silicon, and dirt to avoid printing defects.
Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

Finishing guidelines

When laminating Océ CrystalPoint® prints pressure sensitive laminates are recommended.
A laminator with soft rubber rollers is preferred.
For optimal results temperature should be set between 55-60°C.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.