
Processing Guidelines

Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. It is recommended to handle the media with cotton gloves. Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. Insert the paper with care in the printer. Incorrect loading can cause skewing or creasing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printer ink combinations.

Ink restrictions and printer settings have to be set for specific printer-ink combinations to obtain the best results. Canon media profiles will set recommended ink restrictions and printer settings for Canon supported printers.

Application guidelines

The material will stick to any even and smooth surfaces which are dry and free of dirt, grease, silicon etc. except nonpolar surfaces like PE and PP.

Before gluing it is recommended to check that the surface is appropriate for this aim and that it has been prepared (cleaned) professionally.

When applying the film, the surface temperature should not be below 15 °C.

The media can be used outdoor without lamination when printed with outdoor inks.

However, we recommend protecting its surface if it is subject to abrasion or any other mechanical influences, to dirt or humidity. When dye inks are used, we recommend to always laminate the film to improve the lightfastness and to protect it against smudging.

The film can be removed by heating the surface of the film with a hot air gun. Then pull it off carefully.

Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.