you can
Canon

Large Format Media
Product Information Document

Premium Semi–Glossy 2 – 280g/m² – 2942B

Product Name	Grammage / (g/m²)	Thickness (µ)	Width / mm	Length / m	Mercury Code (EAN128)	POS Code (EAN 13)	Canon iPF5100	Canon iPF6100	Canon iPF6200	Canon iPF6300	Canon iPF6400	Canon iPF6400S/SE	Canon iPF6350	Canon iPF6450	Canon iPF6000S	Canon iPF6300S	Canon iPF8100	Canon iPF8300	Canon iPF8000S	Canon iPF8300S	Canon iPF8400	Canon iPF8400S/SE	Canon iPF9100	Canon iPF9000S	Canon iPF9400	Canon iPF9400S	Canon iPF510	Canon iPF610	Canon iPF605	Canon iPF650	Canon iPF655	Canon iPF710	Canon iPF720	Canon iPF750	Canon iPF755	Canon iPF760	Canon iPF765	Canon iPF810	Canon iPF815	Canon iPF820	Canon iPF825
Premium Semi-Glossy 2	280	290	432	25	2942B020	8714574610399	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v
	280	290	610	25	2942B021	8714574610405		v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v	v		v	v	v	v	v	v	v	v	v	v	v	v	v	v
	280	290	914	25	2942B023	8714574610429											v	v	v	v	v	v	v	v	v	v						v	v	v	v	v	v	v	v	v	v
	280	290	1067	25	2942B022	8714574610412											v	v	v	v	v	v	v	v	v	v												v	v	v	v

Description: This heavy weight premium photographic quality inkjet paper is designed for high end photo printing using both dye and pigment inks. It is instant dry to touch and offers excellent image quality. It is compatible with a large range of dye and pigment digital printing systems, and is the most ideal product for users who need top quality photographic reproductions.

Features: Extremely quick drying, dye and pigment ink compatible, good colour density, excellent image sharpness, smudge resistant, lamination not necessary, easy handling.

Applications: Photography, portraits, posters, graphic art reproductions, exhibition graphics, indoor signage.

Physical Properties:

Weight	278 g/m²	±10
Caliper	290 µm	±12
Curl at 23 °C, 50% RH	0 mm	-20
Gloss (75°)	59%	±6
Opacity	96%	±4
Colour (CIE Lab) D50 /2°	L* 94.5	±1.5
	a* -0.1	±1.0
	b* -2.2	±1.0

Printing : For optimum results select the best possible print settings.

Finishing: To add surface protection from dirt, abrasion and gas-fading, lamination is recommended. Although ink drying is virtually immediate, it is still recommended to allow a waiting time of approximately 3 hours before lamination. In order to prevent moisture ingress and paper splitting, lamination with a 5-6mm encapsulated edge is also recommended. Laminate must be evenly applied to the print in order to avoid curling. Both hot and cold lamination is possible.

Ideal Storage Conditions:

Store paper only in original boxes, out of direct sunlight and under normal climatic conditions (23 °C, 50% RH) until ready to use. Allow material to adapt to room conditions before use.
Papers can absorb moisture in humid conditions or lose moisture in low humidity conditions. Highly humid conditions make the ink drying time longer and this could interfere with proper laminate adhesion.

Shelf Life:

2 years from shipping date when stored under ideal conditions (see a above)